


Typical Properties

Chemical Composition	Polycrystalline β -SiC
Crystal Structure	Diamond Cubic
Geometry	High L/D Rigid Rod Fiber
Mean Diameter, μm	7
Median Length, μm	65-75 (D_{50})
Modulus, GPa	350 (estimated)
Density, g/cm^3	>3.0
Hardness (Mohs)	9.5



Product Description

SI-TUFF™ P-SF is a diamond-like SiC additive used to toughen protective coatings and extend their useful lifetime. It improves abrasion and scratch resistance, thermal conductivity, temperature stability, and hardness. It does this at low loading levels without affecting other desirable properties, including non-stick/release, flexibility, and low friction. Chemically, P-SF is high purity, polycrystalline β -silicon carbide (β -SiC). It has the same cubic crystal structure as diamond and a high aspect ratio, giving it exceptional hardness, mechanical properties, and reinforcing ability. P-SF is chemically inert, will not react with acids and bases, is immune to all solvents, and is temperature stable up to 600°C in air. It has no extractables and is suitable for indirect food contact and is suitable for use in medical devices.

Application Information

If used properly, service life is expected to increase by 20-35%. Critical considerations include selecting the appropriate product grade and form, exercising proper dispersion technique, incorporating into the correct coating layer(s), and using the right loading levels. Haydale Technologies Inc. recommends reviewing the Application Guide for more detailed usage information before beginning your evaluation.

Packaging and Product Handling

P-SF may be supplied as a dry powder, an aqueous dispersion, or a dispersion in resin, oligomer or monomer.

It is recommended to handle dry P-SF powder in a controlled environment. Please consult the SDS (www.Haydale-technologies.com) for additional safety and handling information.

Contact Haydale Technologies Inc.

We believe consultative sales and technical collaboration is the key to success.

Please email us at sales@haydale-technologies.com

Warranty, Limited Remedy, and Disclaimer. Technical information, recommendations and other statements contained in this document or provided by Haydale Technologies Inc. personnel are based on tests or experience that Haydale Technologies Inc. believes are reliable, but the accuracy or completeness of such information is not guaranteed. This information is provided as a convenience and for informational purposes only. Many factors beyond Haydale Technologies Inc. control and uniquely within user's knowledge and control can affect the use and performance of this product in a particular application. User is solely responsible for evaluating this product and determining whether it is a fit for a particular purpose and suitable for user's method of application. Haydale Technologies Inc. makes no warranties or conditions, express or implied, including, but not limited to, any implied warranty or condition of merchantability or fitness for a particular purpose or any implied warranty or condition arising out of a course of dealing, custom or usage of trade. In no event is Haydale Technologies Inc. responsible for, and Haydale Technologies Inc. does not accept and hereby disclaims liability for any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.