


Typical Properties

Chemical Composition	Single-Crystal β -SiC
Crystal Structure	Diamond Cubic
Geometry	High L/D Rigid Rod Microfiber
Mean Diameter, μm	0.65
Mean Length, μm	10-12 (D_{50})
Modulus, GPa	450 (estimated)
Density, g/cm^3	3.21
Hardness (Mohs)	9.5



Product Description

SI-TUFF™ P-SWE is a diamond-like SiC additive used to toughen protective coatings and extend their useful lifetime. It improves abrasion and scratch resistance, thermal conductivity, temperature stability, and hardness. It does this at low loading levels without affecting other desirable properties, including non-stick/release, flexibility, and low friction.

Chemically, P-SWE is high purity, single crystal β -silicon carbide (β -SiC). It has the same cubic crystal structure as diamond and a high aspect ratio, giving it exceptional hardness, mechanical properties, and reinforcing ability.

Epoxy-functionality allows P-SWE to chemically lock into the polymer matrix. This can increase performance in compatible reactive coating systems. P-SWE can interact in complex ways with your coating system, and in many applications can degrade performance.

Application Information

If used properly, service life is expected to increase by 20-35%. Critical considerations include selecting the appropriate product grade and form, exercising proper dispersion technique, incorporating into the correct coating layer(s), and using the right loading levels. Haydale Technologies Inc. recommends reviewing the Applications Guide for more detailed usage information before beginning your evaluation.

Packaging and Product Handling

SI-TUFF™ P-SWE is produced commercially today and is available immediately for purchase. It can be packaged as a dry powder, an aqueous dispersion, or a dispersion in resin, oligomer or monomer. Powder is packaged in 50lb (22.7kg) bags contained in fiber drums. Aqueous dispersions are packaged in 400lb (181kg) steel drums. Smaller quantities are available for purchase for development purposes.

Dry P-SWE powder is a respirable fiber and it is recommended to be handled in a controlled environment. Please consult the SDS (www.Haydale-technologies.com) for additional safety and handling information.

Contact Haydale Technologies Inc.

We believe consultative sales and technical collaboration is the key to success. Please email us at sales@haydale-technologies.com

Warranty, Limited Remedy, and Disclaimer. Technical information, recommendations and other statements contained in this document or provided by Haydale Technologies Inc. personnel are based on tests or experience that Haydale Technologies Inc. believes are reliable, but the accuracy or completeness of such information is not guaranteed. This information is provided as a convenience and for informational purposes only. Many factors beyond Haydale Technologies Inc. control and uniquely within user's knowledge and control can affect the use and performance of this product in a particular application. User is solely responsible for evaluating this product and determining whether it is a fit for a particular purpose and suitable for user's method of application. Haydale Technologies Inc. makes no warranties or conditions, express or implied, including, but not limited to, any implied warranty or condition of merchantability or fitness for a particular purpose or any implied warranty or condition arising out of a course of dealing, custom or usage of trade. In no event is Haydale Technologies Inc. responsible for, and Haydale Technologies Inc. does not accept and hereby disclaims liability for any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.